

## (C) WPI / DERWENT

AN - 81-06781D [05]  
PR - JP790060078 790515  
TI - Wood preservative mixable with plywood adhesive - comprises bis (trichloromethyl) sulphone and opt. tri:alkyl or tri:allyl tin cpd.  
IW - WOOD PRESERVE MIX PLYWOOD ADHESIVE COMPRISE DI SULPHONE OPTION TRI ALKYL TRI ALLYL TIN COMPOUND  
PA - (YOSH ) YOSHITOMI PHARM IND KK  
PN - JP55152003 A 801127 DW8105 000pp  
IC - A01N47/02 ; A01N55/04 ; B27K3/34  
AB - J55152003 The wood preservative includes bis(trichloromethyl)sulphone or bis(tribromomethyl)sulphone, and opt. further includes trialkyl tin compound or triallyl tin. The adhesive strength is not decreased while the preservative penetrates into the wood. The tin compound is pref. bistributyl tin oxide, tributyl tin laurate, tributyl tin palmitate, tributyl tin stearate, tributyl tin phthalate, bistriethyl tin oxide, bistripropyl tin oxide, etc. The adhesive is e.g. phenol-formaldehyde resin, melamine-formaldehyde resin, urea-formaldehyde resin, urea-melamine-formaldehyde resin, resorcinol-formaldehyde resin, etc.